

PRINTOCOLL Z

code 307200

technical information

Water-based adhesive suitable for the transfer of metallized films. The main features of **Printocoll Z** are: high washing resistance, very good brightness of the transfer.

Always test before using in production

PREPARATION

Ready to use

SCREEN FABRICS

34-43 threads/cm.

DRYING

Drying at 90-130°C for 3 minutes.

TRANSFER

Calender: 6-15 m/minute at 140°C.

Heat press: 130-150°C for 15-10 seconds.

Peel off after cooling

WASH-UP

Screens and equipment can be washed with water.

STORAGE

Protect from extremes of temperature. Beware of frost

STANDARD PACKING

Plastic containers Kg 1-5-20-50

APPLICATIONS

cotton, blend cotton, acetate, etc.

SCREEN FABRICS

24-43 fili/cm

EMULSION

DIWOSOL W, DIWOSOL DUAL, DIWOSOL 400

RETARDERS AND THICKENERS

RETARDER 03, GEL RETARDER 04, THICKENER 420

DRYING

at 90-130°C for 3 minutes

TRANSFER

heat press: 130-150°C 15-10 seconds 6 atm - calender: 140°C
6-15 m/minute

WASH-UP

water